

# Hargrave Porcelain Range

Travertine-effect porcelain paving with a structured, high slip-resistance surface.

|                                        |                                |                                  |                         |
|----------------------------------------|--------------------------------|----------------------------------|-------------------------|
| MATERIAL<br>Coloured-body<br>porcelain | APPLICATION<br>Exterior floors | SLIP RATING<br>R11 · PTV 36+ wet | COLOURS<br>Cream, Ivory |
|----------------------------------------|--------------------------------|----------------------------------|-------------------------|

## 01 SIZES

|                    |                         |                   |                                 |
|--------------------|-------------------------|-------------------|---------------------------------|
| 1200 × 600 × 20 mm | RECTIFIED<br>STRUCTURED | 600 × 300 × 20 mm | BULLNOSE &<br>SQUARE EDGE TRIMS |
|--------------------|-------------------------|-------------------|---------------------------------|

## 02 COLOURS



CREAM



IVORY

## 03 PACKING

# Box & Pallet Data

| SIZE                             | BOX   |                |       | PALLET |                |       |
|----------------------------------|-------|----------------|-------|--------|----------------|-------|
|                                  | TILES | M <sup>2</sup> | KG    | BOXES  | M <sup>2</sup> | KG    |
| 1200 × 600 × 20 mm               | 1     | 0.72           | 32.5  | 36     | 25.92          | 1170  |
| Trim · 600 × 300 × 20 mm         | 1     | 0.18           | 8.125 | 100    | 18             | 812.5 |
| Trim corner · 600 × 300 × 20 mm  | 1     | 0.135          | 6.1   | 100    | 13.5           | 610   |
| Grate · 600 × 150 × 20 mm        | 2     | 0.18           | 8     | 100    | 18             | 800   |
| Grate corner · 600 × 150 × 20 mm | 2     | 0.1575         | 7     | 100    | 15.75          | 700   |

## 04 PERFORMANCE

# Technical Details

| TECHNICAL FEATURE  | TEST METHOD    | REQUIRED VALUE           | AVERAGE VALUE              |
|--------------------|----------------|--------------------------|----------------------------|
| Water absorption   | ISO 10545-3    | ≤ 0.5%                   | ◆ 0.05%                    |
| Breaking strength  | ISO 10545-4    | S ≥ 1300 N               | ◆ 13,600 N                 |
| Modulus of rupture | ISO 10545-4    | R ≥ 35 N/mm <sup>2</sup> | ◆ 50 N/mm <sup>2</sup>     |
| Frost resistance   | ISO 10545-12   | No alteration            | ◆ Resistant                |
| Slip resistance    | DIN EN 16165-B | –                        | ◆ R11                      |
| Slip (pendulum)    | BS EN 16165-C  | –                        | ◆ PTV 36+ wet              |
| Shade variation    | ANSI A137.1    | As declared              | ◆ V3 · Moderate            |
| Reaction to fire   | EN 13501-1     | CPR (EU) 305/2011        | ◆ A1 (wall) · A1fl (floor) |

We reserve the right to make product changes. Illustrations may be examples and may differ in appearance from the goods supplied. Errors and misprints excepted. Our general terms and conditions apply to the conclusion of any order.

VERSION 10/26